

**ABSTRACT OF THE DISCLOSURE**

A metal layer is formed by means of an electroless plating process, wherein a surface region of an underlying material is catalytically activated in that a catalyst is deposited or incorporated by CVD, PVD or ALD during and/or after the deposition of the underlying material. In this way, superior metal seed layers may be formed even in high aspect ratio vias of metallization structures.

5